

Contacts

Kuraray Co., Ltd.

Sheets Marketing and Sales Department
Methacrylate Division
OTE CENTER BLD., 1-1-3, Otemachi, Chiyoda-ku, Tokyo 100-8115, Japan
TEL : +81 3 6701 1526, FAX : +81 3 6701 1577
E-mail : psf@kuraray.co.jp

Kuraray Trading Co., Ltd.

Methacrylic Products Division
OTE CENTER BLD., 1-1-3 Otemachi, Chiyoda-ku , Tokyo 100-0004, Japan
TEL : +81 3 6701 2043, FAX : +81 3 6701 2143
E-mail : psf@kuraray.co.jp


Kuraray America, Inc.

2625 BAY AREA BLVD STE 600 HOUSTON TX 77058, U.S.A.
TEL : +1 281 283 1711, FAX : +1 281 283 1722
E-mail : psf@kuraray.co.jp

<http://Kuraraypsf.jp/>

Plastic Scintillating Fibers

Scintillating Fibers
Wavelength Shifting Fibers
Clear Fibers



Kuraray's Plastic Scintillating Fibers

The history of Kuraray's scintillating fiber dates back to 1985, we started to produce the plastic scintillating fibers. Then wavelength shifting fibers and clear optical fibers were put on the market in 1990.

Having excellent stability of properties, Kuraray's plastic fibers are trusted by many scientists and technical experts.

As a pioneer in the world, we developed multi-cladding fibers which have 50% higher light yield than previous single cladding fibers in 1993.

It is well-known that Multi-cladding fibers contributed to improve the properties of fiber detectors in the field of high energy physics.

Bundling several μm ~several hundred μm thin fibers together, which we call multi-fiber was also developed in the past.

Kuraray's plastic fibers play an active part not only in the scene of high energy physics, astrophysics, but in the scene of atomic energy.

We hope to attract attention in the fields of medicine.

There is strong potential for new applications in the future.

This brochure presents only basic technical data.

If you have further questions, please let us know at any time.

We are looking forward to supporting your works and applications.

Index

Plastic Scintillating Fibers - Materials and Structures - **- P3-4**

Scintillating Fibers **- P5-6**

Wavelength Shifting Fibers **- P7-9**

Clear Fibers **- P10**



How to Specify Fibers

In order to specify fibers, the following points must be clarified.

- Description
- Cross-section(Round or Square)
- Cladding(Single or Multi)
- Non-S type or S type
- Length and Dimension
- Cane or Spool
- Concentration of dye must be clarified in 3HF fiber and WLS fibers.

Examples of writing are as follows:

- SCSF-3HF(1500)M,1.0mmD., 2000m, BSJ
→Round fiber, Multi-cladding, S type, 1.0mm diameter, 2000m length. Fiber is put on spool, and the concentration of 3HF dye is 1500ppm.
- Y-11 (200), 0.5mmD.,10000m BJ
→Round fiber, Single cladding, Non-S type, 0.5mm diameter, 10000m length. Fiber is put on spools, the concentration of WLS dye is 200ppm.
- Clear-PS, 0.83mmSQ., 3m, CSJ
→Square fiber, Single cladding, S type, 0.83mm square, 3m length cane.

How to identify the fibers specifications

SCSF-3HF	(1500)	M	1.00mm D	2000m	B	S	J
Y	- 11	(200)	1.50mm SQ	2.50m	C		J

- High purity (all product)
- Type of polymer orientation of PS core
S: S type
No mark: Standard non-S type
- Delivery configuration
B: spool type
C: cane type
- Length of the fiber
- Cross-sectional shape of the fiber
D: Round fiber
SQ: Square fiber
- Diameter of the fiber
- Type of the cladding
M: Multi-cladding
No mark: Single cladding
- Concentration of the dye in ppm for 3HF scintillating and all wavelength shifting
- Grade of the fiber
Scintillating: 7B, 81, 3HF
Wavelength shifting: 2, 3, 7, 8, 11
Clear: PS
- Type of the fiber
Scintillating: SCSF
Wavelength shifting: Y, B, O, R
Clear: Clear




Plastic Scintillating Fibers

- Materials and Structures -

Materials

	Materials	Refractive index	Density (g/cm ³)	No. of atom per cm ³
Core	Polystyrene(PS)	n ₀ =1.59	1.05	C: 4.9x10 ²² H: 4.9x10 ²²
Cladding	for single cladding inner for multi-cladding	Polymethylmethacrylate (PMMA)	n ₀ =1.49	C: 3.6x10 ²² H: 5.7x10 ²² O: 1.4x10 ²²
	outer for multi-cladding	Fluorinated polymer (FP)	n ₀ =1.42	

Cross-section and Cladding Thickness


	Single Cladding	Multi-Cladding (M)
Round Fiber (D)	 <p>Cladding Thickness¹⁾: T=2% of D Numerical Aperture : NA=0.55 Trapping Efficiency : 3.1%</p>	 <p>Cladding Thickness²⁾: T=2%(To)+2%(Ti) =4% of D Numerical Aperture : NA=0.72 Trapping Efficiency : 5.4%</p>
Square Fiber (SQ)	 <p>Cladding Thickness : T=2% of S Numerical Aperture : NA=0.55 Trapping Efficiency : 4.2%</p>	Not available

1) In some cases, cladding thickness T is 3% of D. 2) In some cases, cladding thickness T is 6% of D, To and Ti are both 3% of D.

Cladding and Transmission Mechanism


Single cladding

Single cladding fiber is standard type of cladding.



Multi-cladding

Multi-cladding fiber(M) has higher light yield than single cladding fiber because of large trapping efficiency. Clear-PS fiber of this cladding has extremely higher NA than conventional PMMA or PS fiber, and very useful as light guide fiber. Multi-cladding fiber has long attenuation length equal to single cladding fiber.



Materials / Structures

Type of Polymer Orientation of PS Core

Standard type (Non-S type)

PS core is almost no oriented polystyrene chain and is optically isotropic and very transparent. This conventional standard type has good attenuation length, but it shows weakness against clacking caused by bending or handling during assembling.

S type (S)

Core has molecular orientation along drawing direction. This fiber is mechanically stronger against clacking at the cost of transparency. The attenuation length of this type is nearly 10% shorter than standard type.

Dimensions and Tolerance

Cross-sectional Dimension

Minimum : 0.2mm
Maximum : 2.0mm, typically as follows.
Round (Single and Multi-Cladding) : 0.2, 0.5, 1.0, 1.5, 2.0mm dia.
Square (Single Cladding) : 0.2x0.2, 0.5x0.5, 1.0x1.0, 2.0x2.0mm side



Tolerance of Diameter

Cut Fiber (1-5m long) :
 $\frac{\Delta D}{D} < 2.0\%$ for round fiber
 $\frac{\Delta S}{S} < 3.0\%$ for square fiber
Endless Spool Fiber :
 $\frac{3\sigma}{D} < 2.5\%$ (σ : rms, Spool Dia. : 900mm)

Bending Loss and Minimum Bending Diameter

Bending Loss

The following figure shows bending loss of Clear-PSM and Clear-PSMS. S type is better than Non-S type. The rapid increase of bending loss of non-S type is due to cracking of core. S type does not show such cracking.



Minimum Bending Diameter

We recommend minimum bending diameter as the following table on safety side and long term reliability.

Type	2mmΦ Fiber	1mmΦ Fiber	0.5mmΦ Fiber
S type	200mm	100mm	50mm
Non-S type	400mm	200mm	100mm

Scintillating Fibers

Formulations¹⁾

Description	Color	Emission Spectra		Decay Time [ns]	Att.Leng. ²⁾ [m]	Characteristics
		Peak[nm]	Peak[nm]			
SCSF-78	blue	See the following figure	450	2.8	>4.0	Long Att. Length and High Light Yield
SCSF-81	blue		437	2.4	>3.5	Long Attenuation Length
SCSF-3HF(1500)	green		530	7	>4.5	3HF formulation for Radiation Hardness

1) Test fibers are Non-S type, 1mmφ.

2) Measured by using bialkali PMT and UV light(254nm).


Quality control is made by another measurement of the transmission loss every batch.

Attenuation Length Measurement

We routinely measure attenuation length by 3m fiber sample for all production.

The attenuation curve (for example) in the figure is approximated by the one exponential expression

$I(x) = I_0 \exp(-\frac{x}{\lambda})$ except very near distance. The attenuation length λ is calculated using the data between $x=100\text{cm}$ and $x=300\text{cm}$.



About "Export Trade Control Order"

The scintillating fiber is assigned in article 1 of the Export Trade Control Order as undermining the maintenance of international peace and safety.

To export this item, an approval of the Minister of Economy, Trade and Industry of Japan is required, so we need to confirm the end user and application for each sales.

We may sell the fibers to you, but we would have to check and confirm the end user and application everytime we have an inquiry from you, and we may not be able to accept some inquiries depending on the end user and application.




SCSF-78 / SCSF-81 / SCSF-3HF(1500)


Technical Data

Emission Spectra



SCSF-78



SCSF-81




SCSF-3HF(1500)




Transmission Loss


SCSF-78



SCSF-81




SCSF-3HF(1500)



Wavelength Shifting Fibers

Y-7(100) / Y-8(150) / Y-11(200)
B-2(200) / B-3(200) / O-2(100)




Formulations¹⁾

Description	Color	Emission		Absorption Peak [nm]	Att. Leng. ²⁾ [m]	Characteristics
		Spectra	Peak [nm]			
Y-7(100)	green	See the following figure	490	439	>2.8	Blue to Green Shifter
Y-8(100)	green		511	455	>3.0	Blue to Green Shifter
Y-11(200)	green		476	430	>3.5	Blue to Green Shifter (K-27 formulation) Long Attenuation Length and High Light Yield
B-2(200)	blue		437	375	>3.5	UV to Blue shifter
B-3(200)	blue		450	351	>4.0	UV to Blue shifter
O-2(100)	orange		550	535	>1.5	Green to orange shifter
R-3(100)	red		610	577	>2.0	Green to red shifter

1) Test fibers are Non-S type, 1mmφ.

2) Measured by using bialkali PMT.


Attenuation length measurement method is the same with scintillating fibers which can be confirmed on Page 5.




Technical Data

Emission Spectra


Y-7(100)




Y-8(150)




Y-11(200)




B-2(200)



B-3(200)



O-2(100)




Wavelength Shifting Fibers

Y-7 / Y-8 / Y-11 / B-2 / B-3 / O-2 / R-3


Technical Data

Absorption and Emission Spectra


Y-7, Y-8, Y-11



B-2, B-3




O-2, R-3




Transmission Loss


Y-7, Y-8, Y-11



B-2, B-3



O-2, R-3



Clear Fibers

Clear-PS



Formulations¹⁾

Description	Emission Spectra		Att.Leng. [m]	Characteristics
	Color	Peak[nm]		
Clear-PS	—	—	>10	depend on wavelength

1) Test fibers are Non-S type, 1mmφ.

Technical Data

Transmission Loss



All data presented herein is based on actual measurements performed by Kuraray Co., Ltd. Kuraray Co., Ltd. accepts no liability for damage or loss resulting from the use or misuse of this information.